



Package	Part No.	Chip		Lens Appearance	Absolute Maximum Ratings			Electro-optical Data(At 2mA)			Viewing Angle 2θ 1/2 (deg)	Drawing No.
		Material/ Emitted Color	Peak Wave Length λ p (nm)		Δ λ (nm)	Pd (mw)	If (mA)	Vf (V)		Iv (mcd)		
								Typ	Max			
T-1 Standard 1.0" Lead 3 φ	BL-B5131-L	GaP/GaP/ Bright Red	700	Red Diffused	90	10	5	1.9	2.2	1.0	40	L-144
	BL-B4531-L	GaAsP/GaP/ Hi-Eff Red	635		45	10	5	1.8	2.2	6.0		
	BL-B2131-L	GaP/GaP/ Green	568	Green Diffused	30	10	5	1.9	2.2	6.0		
	BL-BX1131-L	GaP/GaP/ Hi-Eff Green	568		30	10	5	1.8	2.2	8.0		
	BL-B3131-L	GaAsP/GaP/ Yellow	585	Yellow Diffused	35	10	5	1.9	2.2	4.0		
	BL-B4131-L	GaAsP/GaP/ Orange	635	Orange Diffused	45	10	5	1.8	2.2	6.0		
BL-B4331-L	GaAsP/GaP/ Orange	635	Water Clear	45	10	5	1.8	2.2	12.0	30		
T-1 Standard 1.0" Lead 3 φ	BL-B5141-L	GaP/GaP/ Bright Red	700	Red Diffused	90	10	5	1.9	2.2	1.0	40	L-145
	BL-B4541-L	GaAsP/GaP/ Hi-Eff Red	635		45	10	5	1.8	2.2	6.0		
	BL-B2141-L	GaP/GaP/ Green	568	Green Diffused	30	10	5	1.9	2.2	6.0		
	BL-BX1141-L	GaP/GaP/ Hi-Eff Green	568		30	10	5	1.8	2.2	8.0		
	BL-B3141-L	GaAsP/GaP/ Yellow	585	Yellow Diffused	35	10	5	1.9	2.2	4.0		
	BL-B4141-L	GaAsP/GaP/ Orange	635	Orange Diffused	45	10	5	1.8	2.2	6.0		
BL-B4341-L	GaAsP/GaP/ Orange	635	Water Clear	45	10	5	1.8	2.2	12.0	30		
T-1 Low Profile 1.0"Lead 5 φ	BL-B4531E-L	GaAsP/GaP/ Hi-Eff Red	635	Red Diffused	45	10	5	1.8	2.2	30.0	45	L-146
	BL-B2131E-L	GaP/GaP/ Green	568	Green Diffused	30	10	5	1.9	2.2	30.0		
	BL-B3131E-L	GaAsP/GaP/ Yellow	585	Yellow Diffused	35	10	5	1.9	2.2	20.0		
	BL-B2431E-L	GaP/GaP/ Green	568	Green Trans	30	10	5	1.9	2.2	65.0	40	
	BL-B3431E-L	GaAsP/GaP/ Yellow	585	Yellow Trans	35	10	5	1.9	2.2	55.0		
	BL-B2331E-L	GaP/GaP/ Green	568	Water Clear	30	10	5	1.9	2.2	65.0		
BL-B3331E-L	GaAsP/GaP/ Yellow	585	35		10	5	1.9	2.2	55.0			
T-1 Low Profile 1.0"Lead 5 φ	BL-B4531K-L	GaAsP/GaP/ Hi-Eff Red	635	Red Diffused	45	10	5	1.8	2.2	30.0	45	L-147
	BL-B2131K-L	GaP/GaP/ Green	568	Green Diffused	30	10	5	1.9	2.2	30.0		
	BL-B3131K-L	GaAsP/GaP/ Yellow	585	Yellow Diffused	35	10	5	1.9	2.2	20.0		
	BL-B2431K-L	GaP/GaP/ Green	568	Green Trans	30	10	5	1.9	2.2	65.0	40	
	BL-B3431K-L	GaAsP/GaP/ Yellow	585	Yellow Trans	35	10	5	1.9	2.2	55.0		
	BL-B2331K-L	GaP/GaP/ Green	568	Water Clear	30	10	5	1.9	2.2	65.0		
BL-B3331K-L	GaAsP/GaP/ Yellow	585	35		10	5	1.9	2.2	55.0			
T-13/4 Standard 1.0" Lead 5 φ	BL-B5134-L	GaP/GaP/ Bright Red	700	Red Diffused	90	10	5	1.9	2.2	3.5	35	L-148
	BL-B4534-L	GaAsP/GaP/ Hi-Eff Red	635		45	10	5	1.8	2.2	4.5		
	BL-B2134-L	GaP/GaP/ Green	568	Green Diffused	30	10	5	1.9	2.2	4.5		
	BL-BX1134-L	GaP/GaP/ Hi-Eff Green	568		30	10	5	1.8	2.2	5.0		
	BL-B3134-L	GaAsP/GaP/ Yellow	585	Yellow Diffused	35	10	5	1.9	2.2	4.0		
	BL-B4134-L	GaAsP/GaP/ Orange	635	Orange Diffused	45	10	5	1.8	2.2	5.0		
BL-B4334-L	GaAsP/GaP/ Orange	635	Water Clear	45	10	5	1.8	2.2	12.0	12		
T-13/4 Standard 1.0" Lead 5 φ	BL-B5134-1-L	GaP/GaP/ Bright Red	700	Red Diffused	90	10	5	1.9	2.2	2.5	40	L-149
	BL-B4534-1-L	GaAsP/GaP/ Hi-Eff Red	635		45	10	5	1.8	2.2	3.5		
	BL-B2134-1-L	GaP/GaP/ Green	568	Green Diffused	30	10	5	1.9	2.2	3.5		
	BL-BX1134-1-L	GaP/GaP/ Hi-Eff Green	568		30	10	5	1.9	2.2	4.0		
	BL-B3134-1-L	GaAsP/GaP/ Yellow	585	Yellow Diffused	35	10	5	1.9	2.2	3.0		
	BL-B4134-1-L	GaAsP/GaP/ Orange	635	Orange Diffused	45	10	5	1.8	2.2	3.5		
BL-B4334-1-L	GaAsP/GaP/ Orange	635	Water Clear	45	10	5	1.8	2.2	10.0	20		
T-13/4 Standard 1.0" Lead 5 φ	BL-B5134G-1-L	GaP/GaP/ Bright Red	700	Red Diffused	90	10	5	1.9	2.2	2.0	45	L-150
	BL-B4534G-1-L	GaAsP/GaP/ Hi-Eff Red	635		45	10	5	1.8	2.2	3.0		
	BL-B2134G-1-L	GaP/GaP/ Green	568	Green Diffused	30	10	5	1.9	2.2	3.0		
	BL-BX1134G-1-L	GaP/GaP/ Hi-Eff Green	568		30	10	5	1.9	2.2	4.0		
	BL-B3134G-1-L	GaAsP/GaP/ Yellow	585	Yellow Diffused	35	10	5	1.9	2.2	2.0		
BL-B4334G-1-L	GaAsP/GaP/ Orange	635	Water Clear	45	10	5	1.8	2.2	8.0	25		
T-13/4 Flangeless 1.0" Lead 5 φ	BL-B5134N-1-L	GaP/GaP/ Bright Red	700	Red Diffused	90	10	5	1.9	2.2	2.0	45	L-151
	BL-B4534N-1-L	GaAsP/GaP/ Hi-Eff Red	635		45	10	5	1.8	2.2	3.0		
	BL-B2134N-1-L	GaP/GaP/ Green	568	Green Diffused	30	10	5	1.9	2.2	3.0		
	BL-BX1134N-1-L	GaP/GaP/ Hi-Eff Green	568		30	10	5	1.8	2.2	3.5		
	BL-B3134N-1-L	GaAsP/GaP/ Yellow	585	Yellow Diffused	35	10	5	1.9	2.2	3.0		

Remark : 1.Hi-Eff Red / High-Efficiency Red.  
 2.Trans / Transparent.  
 3.2θ 1/2 The off-axis angle at which the luminous intensity is half the axial luminous intensity.



<p><b>L-144</b>      <b>BL-Bxx31-L Series</b></p>	<p><b>L-145</b>      <b>BL-Bxx41-L Series</b></p>
<p><b>L-146</b>      <b>BL-Bxx31E-L Series</b></p>	<p><b>L-147</b>      <b>BL-Bxx31K-L Series</b></p>
<p><b>L-148</b>      <b>BL-Bxx34-L Series</b></p>	<p><b>L-149</b>      <b>BL-Bxx34-1-L Series</b></p>
<p><b>L-150</b>      <b>BL-Bxx34G-1-L Series</b></p>	<p><b>L-151</b>      <b>BL-Bxx34N-1-L Series</b></p>

Notes : 1.All Dimensions are in millimeters (inches).  
 2.Tolerance is  $\pm 0.25\text{mm}$  (.010").